


HPDR

波纹管

Corrugated conduit

+90°C +194°F
-50°C -58°F

Material: PA12 MOD R



- 适用于需要持续动态运动的场合
- 厚壁型
- 不含卤素和镉
- 动态抗疲劳性能优异
- 机械强度性能优异
- 耐候性能优异

- suitable for continuous dynamic flexing movements, heavy version
- with increased wall thickness
- free of halogen and cadmium
- excellent fatigue strength
- excellent mechanical strength characteristics
- excellent weathering performances

温度范围 / Temperature range
弯曲性能 / 柔性 / Flexibility/Ductility
动态性能 / Dynamic
机械防护性能 / Mechanical protection
防火性能 / Fire precaution performance
耐化学品性能 / Chemical resistance
耐候性 / Resistance to weathering

min.		max.	
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■
■	■	■	■



产品号 Part No. ¹⁾		名义尺寸 Nominal width	波型 Profile ²⁾	尺寸 Dimensions in mm (nom.)		弯曲半径 Bending radius in mm		包装单元 PU
黑色 / black	灰色 / grey	NW		内径 / ID	外径 / OD	stat. R.	dyn. R.	m
HPDRC-29B.50	HPDRC-29G.50	29	C	28,3	34,7	50	120	50
HPDRC-36B.25	HPDRC-36G.25	36	C	36,6	42,3	60	180	25
HPDRC-48B.25	HPDRC-48G.25	48	C	47,0	54,4	70	210	25
HPDRC-48B.30	HPDRC-48G.30	48	C	47,0	54,4	70	210	30
HPDRC-56B.25	HPDRC-56G.25	56	C	56,3	67,2	120	260	25
HPDRC-70B.25	HPDRC-70G.25	70	C	67,2	79,6	150	340	25
HPDRC-70B.30	HPDRC-70G.30	70	C	67,2	79,6	150	340	30
HPDRC-95B.10	HPDRC-95G.10	95	C	91,3	106,0	230	450	10

您可以通过以下地址查询更多的技术信息 / You can find more technical information here

CADENAS – eCATALOGsolutions elektronischer CAD Katalog / eCATALOGsolutions electronic CAD catalog: <https://fraenkische-ip.partcommunity.com>

¹⁾ FIPMOTION® 波纹管编码规则 / Part numbering key for FIPMOTION® corrugated conduits: www.fraenkische-ip.com/fipmotion-part-no

²⁾ 波纹管波型 / Conduit profiles: www.fraenkische-ip.com/fipsystems-profiles



HPDR 产品性能 / Product performances

应用性能 <i>Application performances</i>	特性 <i>Characteristics</i>	单位 <i>Unit</i>	规范标准 <i>Standards, specifications</i>	备注 <i>Remark</i>
温度范围 / <i>Temperature range</i>	-45 到 / <i>to</i> +90 -49 到 / <i>to</i> +194	°C °F	IEC EN 61386	
温度范围 / <i>Temperature range</i>	-50 到 / <i>to</i> +90 -58 到 / <i>to</i> +194	°C °F	IS FIP	
温度 (短周期) / <i>Temperature (short-term)</i>	150 (500 h); 165 (100 h) 302 (500 h); 329 (100 h)	°C °F	IS FIP	
填充率 (最大) / <i>Filling ratio (max.)</i>	70	%	IS FIP	
机械性能 / <i>Mechanical performances</i>				
峰值负载 / <i>Peak load value</i>	320	N	IS FIP	
拔脱强度 / <i>Pull out strength</i>	460	N	IS FIP	
防火性能 / <i>Fire safety performances</i>				
不含卤素和镉 <i>Free from halogens and cadmium</i>	是 / <i>yes</i>			
阻燃等级 / <i>Fire classification</i>	V2		UL 94	
耐候性 / <i>Weathering performances</i>				
UV- 及耐候性能 <i>UV and weathering performance</i>	优异 <i>excellent</i>		IS FIP	可达 30 年 <i>up to 30 years</i>

测试条件参照EN ISO 139 , 温度 23°C / 湿度50% r. F. (如未注明测试条件). IS FIP = FIP内部测试规范
Tests carried out acc. EN ISO 139 at 23°C / 50% r. h. (if not indicated differently). IS FIP = Internal Specification FIP

我们尽我们的知识水平所提供的数据, 图片和技术规格图档反映了当前的工程技术水平。这不包含对最后应用有关的任何责任。产品用户需根据应用要求自行进行评估。以确定产品是否符合特殊应用条件。我们对产品的责任只考虑一般规定条件下的水平。FIP保留对产品数据和数值进行技术调整的权力。例如更改材料和加工工艺, 在保证产品性能数值不下降的情况下不会另行通知。

The provided data, images and technical specification drawings reflect the current engineering level and are to the best of our knowledge. This does not include any liability regarding the final application. Users of the products have to make their own evaluation to determine the suitability for a specific application. Our liability for these products considers the stated level within our General Conditions only. FRAENKISCHE Industrial Pipes (FIP) reserves the right to adjust specified data and values as well as implementing technical adjustments of the products e. g. change of materials and processing technologies without prior notice as long as the specified values are not reduced.