


2PAS-O

可分型双层波纹管
Divisible corrugated conduit

+120°C / +248°F
-50°C / -58°F

Material: PA6 MOD BS 橙色 / orange
色号 RAL2003 / similar to RAL2003



- 用于线缆线束需要单独标记的情况
 - 自熄, 不含卤素和镉
 - 耐候性能良好
 - 防火性能好
 - 双层结构提供了更高的抗冲击性能
- for applications in which cables or wires have to be marked separately
 - self-extinguishing, free of halogen and cadmium
 - average to good weathering performances
 - increased fire safety performances
 - double shell conduit properly overlaps and provides enhanced cable protection against external impacts

温度范围 / Temperature range
弯曲性能 / 柔性 / Flexibility/Ductility
动态性能 / Dynamic
防火性能 / Fire precaution performance
耐化学品性能 / Chemical resistance
耐候性 / Resistance to weathering

min.					max.



产品号 Part No. ¹⁾	名义尺寸 Nominal width	波型 Profile ²⁾	尺寸 Dimensions in mm (nom.) ³⁾		弯曲半径 Bending radius in mm	包装单元 PU
			内径 / ID	外径 / OD		
橙色色号 RAL2003 / similar to RAL2003	NW				stat. R.	m
2PASM-0702.50	07	M	6,3	10,0	25	50
2PASM-1002.50	10	M	8,8	13,5	30	50
2PASM-1102.50	11	M	11,0	16,1	30	50
2PASM-1402.50	14	M	13,2	18,7	35	50
2PASM-1602.50	16	M	16,0	21,5	40	50
2PASM-2002.50	20	M	20,2	25,7	50	50
2PASM-2302.50	23	M	23,9	31,3	60	50
2PASM-2902.25	29	M	27,3	35,5	110	25
2PASM-3702.25	37	M	32,5	43,0	135	25
2PASM-4502.25	45	M	43,1	54,2	140	25
2PASM-7002.10	70	M	67,0	79,8	180	10
2PASM-10002.10	100	M	87,5	102,5	200	10

您可以通过以下地址查询更多的技术信息 / You can find more technical information here

CADENAS - 产品CAD数据目录 / eCATALOGsolutions electronic CAD catalog: <https://fraenkische-ip.partcommunity.com>

¹⁾ FIPSPLIT® 波纹管编码规则 / Part numbering key for FIPSPLIT® corrugated conduits: www.fraenkische-ip.com/fipsplit-part-no

²⁾ 波纹管波型 / Conduit profiles: www.fraenkische-ip.com/fipsystems-profiles

³⁾ 英制尺寸转换 / Conversion to inch: www.fraenkische-ip.com/fipsystems-conversion-inch



2PAS-O 产品性能 / Product performances

应用性能 <i>Application performances</i>	特性 <i>Characteristics</i>	单位 <i>Unit</i>	规范标准 <i>Standards, specifications</i>	备注 <i>Remark</i>
温度范围 / <i>Temperature range</i>	-50 到 / <i>to</i> +120 -58 到 / <i>to</i> +248	°C °F	IS FIP	
填充率 (最大) / <i>Filling ratio (max.)</i>	70	%	IS FIP	推荐值 / <i>Recommendation</i>

机械性能 / <i>Mechanical performances</i>				
峰值负载 / <i>Peak load value</i>	320	N	IS FIP	

防火性能 / <i>Fire safety performances</i>				
不含卤素和镉 / <i>Free from halogens and cadmium</i>	是 / <i>yes</i>		DIN EN ISO 63355:2023-08	
阻燃等级 / <i>Fire classification</i>	V2		UL 94	
氧指数 / <i>Oxygen index</i>	>32	%	EN ISO 4589-2	
火灾危害等级 / <i>Fire hazardous level</i>	HL2 R22 / HL3 R23		EN45545-2	

耐候性 / <i>Weathering performances</i>				
UV- 及耐候性能 <i>UV and weathering performance</i>	一般 <i>average</i>		IS FIP	3 到 5 年 <i>3 to 5 years</i>

测试条件参照EN ISO 139, 温度 23°C / 湿度50% r. h. (如未注明测试条件). IS FIP = FIP内部测试规范
Tests carried out acc. EN ISO 139 at 23°C / 50% r. h. (if not indicated differently). IS FIP = Internal Specification FIP

我们尽我们的知识水平所提供的数据, 图片和技术规格图档反映了当前的工程技术水平。这并不包含对最后应用有关的任何责任。产品用户需根据应用要求自行进行评估。以确定产品是否符合特殊应用条件。我们对产品的责任只考虑一般规定条件下的水平。FIP保留对产品数据和数值进行技术调整的权利。例如更改材料和加工工艺, 在保证产品性能数值不下降的情况下不会另行通知。

The provided data, images and technical specification drawings reflect the current engineering level and are to the best of our knowledge. This does not include any liability regarding the final application. Users of the products have to make their own evaluation to determine the suitability for a specific application. Our liability for these products considers the stated level within our General Conditions only. FRAENKISCHE Industrial Pipes (FIP) reserves the right to adjust specified data and values as well as implementing technical adjustments of the products e. g. change of materials and processing technologies without prior notice as long as the specified values are not reduced.